

Technical Data Sheet

ALBASIA PLYWOOD

1 General Information

Name	Albasia
Scientific Name	Albizia Falcataria
Origin	Indonesia

2 Technical Data

Sap	none
Colouring	Whitely, with yellow-brown paleness
Density (kg/m ³)	abt. 600
Density à 12% (kg/m ³)	abt. 320
Degree of Shrinkage Radial	R = 6.7
Tangential	T = 3.0
Compressive Resistance (N/mm ²)	C12 = 21
Flexural Resistance (N/mm ²)	F12 = 50
Flexural Modulus (N/mm ²)	E12 = 4100

3 Applications

Light Construction
Wooden Battens
Vehicle Construction
Furniture Industry
Caravan Industry
Exhibition Stand Construction

